

- Extremely quick and clean installation
- Installation without glue, hammer or tapping block
- Strong connections at the top and longitudinal edges

Edition 01.2011	Norm	Parameters	Norm requirements	Swiss hardwoods values
Dimensions				
panel				150mm x (400-1200mm)RL
overall thickness				15 mm
m2 per pack				2.64 m2
Panel construction				
Surface layer				3 mm
Coreboard			Multi Plywood	9 mm
Backing layer			Construciton	2 mm
Fixing system		width and lengthwise		Uni-click
Surface layer				
wood species				American Walnut
finishing				UV Lacquer, Satin Finish
grading				ABC Grade
Installation				
floating		On Swiss hardwoods underlay	Cf installation instructions	
glued to subfloor		Swiss hardwoods MS polymer resin	Cf installation instructions	
CE	EN 14342: 2008	notified body	DAP-PL-1033.00	level 4
Warranty		domestic use		lifetime
		commercial use		on request
		Uni-click connection		lifetime
Finishing				
Wear resistance	Rubio Monocoat Hardwork Oils	falling sand S 33		UV Lacquer 7 coats
Scratch resistance	SIS 92350 DIN 6886	anti-scratch Top Coat with nano-technology		500-1250 100-1700
Stain resistance	EN 13442		all except blue ink blue ink	class 5 class 3
General aspect of an installed flooring	EN 13489	lippig - differences in height	≤ 0,20 mm	≤ 0,15 mm
		difference in width	≤ 0,20 mm	≤ 0,15 mm
		cupping lengthwise	≤ 0,1%	≤ 0,1%
		cupping in width	≤ 0,2%	≤ 0,2%
Caster chairs		use soft casters Type W (EN 12529) and / or suitable office mat		
Dimensional stability	ISO 23339 changes 30-85% RH	cupping short side maxi %	≤ 0,30	≤ 0,25
		cupping short side mini %	≥ -0,20	≥ -0,15
		open joints short side (mm)	≤ 0,20	≤ 0,15
		open joints long side (mm)	≤ 0,30	≤ 0,20
Slip resistance	CEN/TS 15676			USRV 50-52
Emission of Formaldehyde	EN 717-1			E1
PCP				below detection limit
Underfloor heating			consult specific installation instructions	