


TECHNICAL INFORMATION

DALI		Norm	Parameters	Norm requirements	Universal values
 Dimensions	Panel		1-strip		1820x145 mm
			3-strip		1820x190 mm
	Overall thickness				12,5 mm
	Panels per pack				6
	m ² per pack			1-strip	1,5834
			3-strip	2,0748	
Panel construction	Surface layer		PEFC, FSC or legally controlled sources		2,5 mm
	Coreboard				HDF
	Backing layer		PEFC, FSC or legally controlled sources	Spruce or Pine	1,35 mm
	Tongue and groove		lengthwise		Uniclic
			width		Uniclic Multifit
Surface layer	Wood species			Oak - Ash	
	Origine			Europe	
	Finishing				Matt lacquer
	Grading				Millrun
Installation	Floating			on underlay	cf installation instructions
	Glued to subfloor			Parquet flooring glue	cf installation instructions
CE	EN 14342: 2008-09		notified body	DAP-PL-1033.00	level 4
PEFC					PEFC label
Warrenty			domestic use	conditions in each pack	25 years
			Uniclic connection		Lifetime
			commercial		on request
Finishing	Finishing	UV-curing varnish			5 to 7 layers
	Wear resistance	SIS 923509	falling sand		800-1000
		DIN 68861	S 33		100-1050
	Scratch resistance		anti-scratch Top Coat with nano-technology		
Stain resistance	EN 13442			all except blue ink	class 5
				blue ink	class 3
General aspect of an installed flooring	EN 13489	lipping - differences in height		≤ 0,20 mm	≤ 0,15 mm
		difference in width		≤ 0,20 mm	≤ 0,15 mm
		cupping lengthwise		≤ 0,1%	≤ 0,1%
		cupping in width		≤ 0,2%	≤ 0,2%
Castor chairs		use soft castors TypeW (EN12529) and/or suitable office mat			
Dimensional stability					
Slip resistance	CEN/TS 15676				USRV 50-52
Emission of Formaldehyde	EN 717-1				E1
PCP					below detection limit
Heat resistance	EN 12664				0,106 m2.K/W
Underfloor heating				consult special installation instructions	
Reaction to fire	EN 14342		CWFT		Dfl-s1